



Certificate of Test

ASTM C150 Type I/II
AASHTO M85 Type I/II

March 7, 2018
Lot 32-59

C150 Chemical Requirements – Table 1

Item	Spec Limit	Result
Al ₂ O ₃	N/A	4.0
Fe ₂ O ₃	N/A	3.1
MgO	6.0 Max	1.2
SO ₃	2.3*	3.4
L.O.I.	3.5 Max	2.6
Insoluble Residue	1.5 Max	1.01

*Does not apply. In compliance with Footnote D, Table 1, ASTM Standard Specification C150 and AASHTO Standard Specification M85.

C150 Physical Requirements – Table 3

Item	Spec Limit	Result
Blaine Specific Surface, m ² /kg	260 Min	407
Air Content of Mortar, Vol %	12 Max	7.6
Autoclave Expansion, %	0.80 Max	0.02
Vicat Initial Time of Set, minutes	45 Min	85
Vicat Final Time of Set, minutes	375 Max	185
Compressive Strength, psi:		
	3 Days	1740 Min 3730
	7 Days	2760 Min 4610
Lot 3-26	28 Days	3050 Min 6200

Compound Composition

Item	Spec Limit	Result
C ₃ A, %	8 Max	5
Inorganic Processing Addt's, %	5.0 Max	0
CaCO ₃ in Limestone, %	70 Min	88.5
Limestone Additions	5.0 Max	4.9
C1038 Mortar Bar Expansion, %	0.020% Max	0.007

This cement has been sampled and tested in accordance with ASTM standard methods and procedures. Cement analysis are reported as oxides, in accordance with ASTM Test Method C114. This cement is manufactured at our Laramie, Wyoming facility. All test results are certified to comply with the type and specification designated. We are not responsible for improper use or workmanship.

Bob Kersey, Chief Chemist



AASHTO Accredited Since 1996